



Revised: 5/2016

AP-6300
LIQUID WALK PAD
COLOR:GREY

PRODUCT DESCRIPTION

ARMOUR PROOF AP-6300 is a single-component, thermoplastic rubber coating with rubber granules for texture and slip resistance, formulated for protecting metal, wood, EPDM, APP, TPO and Hypalon. **AP-6300** provides a waterproof, durable, seamless flexible weather resistant membrane with excellent elongation, tensile strength and UV protection for high traffic areas.

TECHNICAL DATA

TOTAL SOLIDS BY WEIGHT:	69% ± 3%
TOTAL SOLIDS BY VOLUME:	62% ± 3%
DENSITY:	Mean = 10.5 lb/gallon ASTM D-1475
VOC CONTENT:	3.26 lb/gallon
HEAT STABILITY:	Material stable for 10 days at 120° F then re-evaluated
FLASH POINT:	105° F
HARDNESS:	50-60 Shore A
ACCELERATED WEATHERING:	No degradation ASTM G53
TENSILE STRENGTH:	1000 psi ASTM D-412
ELONGATION:	500% ASTM D-412
REFLECTIVITY:	85% White
WATER ABSORPTION:	0.04%
VAPOR TRANSMISSION:	0.025 perms
SHELF LIFE:	12 months @ 40° - 90° F
COLOR:	Gray and Safety Colors
PACKAGING:	5-Gallon Pail

COVERAGE AND DRYING TIME

Apply **AP-6300** by phenolic core roller at a rate of 1 gallon per 17.5 square feet, according to the substrate and condition. Backrolling may be necessary to prevent pinholes. A minimum of 56 mils DFT will result when applying at the recommended 90 mils wet thickness. Mask off the area and pour the coating, rolling out the product at the recommended spread rate. Too thick of a coating will cause solvent entrapment. Cure time is 24-48 hours.

PREPARATION OF SUBSTRATE

Surface must be pressure washed clean, free of all loose particles, dirt debris and other contaminants that could inhibit adhesion. Wire brushing may be recommended in addition to pressure washing the surface. The surface must be completely dry to prevent blistering of the product.

Refer to the Armour Proof Coatings Specification for detailed instructions on how to prepare the specific substrate.

LIMITATIONS AND PRECAUTIONS

Do not apply when temperature is below 40° F during application or drying time. Apply product when relative humidity is below 90° F. Allow for adequate dry times between coats and inclement weather. Higher humidity or lower temperatures will slow down dry times.

WARRANTY

This product will perform as claimed if directions are followed. Armour Proof Coatings cannot control conditions of application and substrate, or methods used. This warranty is limited to replacement of the defective material used, and does not include labor or labor costs.

United Asphalt Company
237 North Grove Street
Williamstown Junction, NJ 08009
800-843-0317
www.armourproofcoating.com